

HYLOMAR L/M/H

Description

Hylomar M is a highly engineered, polyester-urethane based non-setting and non-hardening gasketing compound.

The compound is resistant to a wide range of fluids including industrial fuels, oils, water and brine, air, turbine and piston engine combustion products, water, water/glycol and methanol mixtures, petroleum and synthetic diester lubricating oils, gasoline and kerosene fluids (Avtur and Avcat) and fluorocarbon refrigerants.

Hylomar M can operate at temperatures between -50°C and up to 250°C (-58°F and 482°F).

Hylomar M can be used to seal both joint surfaces and threaded parts.

Typical Properties

Hylomar	L	M	H
Film Thickness	0.015 mm	0.03 mm	0.09 mm
Surface Finish Max	2.0 μm	3.0 μm	3.5 μm
Area covered by 80 mls	2.25 m^2	1.36 m^2	0.67 m^2
Product coverage after drying	2 mg/cm^2	4 mg/cm^2	12 mg/cm^2
Solvent Content	47%	42%	29%
Specific Gravity (ASTM D4659)	0.942	1.035	1.103

Instructions for use

The joint faces should be clean and dry. Both faces should then be coated with a thin even film of the product, and the solvent allowed to evaporate. The components can then be assembled. Since Hylomar M is non-setting, once applied to the faces of the component, immediate assembly is not required. Due to the nature of Hylomar M, re-torquing of assembled components may be required.

For stud loading, torque to required figure, allow compound to settle for a few minutes, then re-torque.

Hylomar M can be removed from dismantled components using Hylomar Cleaner.

Typical applications

Hylomar M enables the effective sealing of metal to metal and plastic to plastic components. Typical applications include water and oil pumps, instrument inspection covers, cylinder heads and sumps, coating pre-formed gaskets, weather proofing motors and outdoor high voltage circuit breakers inlet manifolds, timing case covers, oil pump joints, gear box and transmission components and thread

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.09.2015	Page 1 of 2
	Product name	Hylomar M Issue 10	

sealing. It has also been successfully used in the assembly of gas turbines, water cooled generators and turbo vacuum systems. There is no staining of copper and silver, etc., from traces of volatiles at elevated temperature, and is therefore suitable for joints and threads in close proximity to switch mechanisms.

Hylomar M is harmless to joint materials. It is equally suitable for use as a gasket dressing and for metal to metal application.

Light grade: inlet manifolds, timing case covers, oil pump joints, gearbox and transmission components, thread sealing and any finely machined surface.

Medium grade: water and oil pumps, instrument inspection covers, cylinder heads, sumps and most machined surfaces.

Heavy grade: gas turbines, water cooled generators, turbo vacuum systems, gearboxes and most rough machined surfaces.

Handling and Safety Properties

Hylomar M is highly-flammable

Product contains Acetone

Once the Acetone has evaporated, Hylomar M may be regarded as non-flammable.

Please see product safety data sheet for more information.

Storage Precautions

Store in a cool, dry place between 5°C and 25°C (41°F and 77°F) with adequate ventilation

The shelf life is 2 years when stored in the original unopened containers as detailed above, for all tubes, cartridges, and lever lid tins. The brush top tin has a shelf life of 1 year.

Packaging

Hylomar M is available in 40ml (1.35fl.oz) and 80ml (2.7fl.oz) tubes, 1 litre (33.81fl.oz) tins, 250ml (8.45fl.oz) brush top tins and 300ml (10.14fl.oz) cartridges. Hylomar M is also available as an Aerosol.

Information given in this publication is based upon technical data gained in our own and other Laboratories and is believed to be true. However the material is used in conditions beyond our control thus we can assume no liability for results obtained or damages incurred through the application of the data present herein.

Hylomar Ltd, Cale Lane, Wigan WN2 1JT UK Tel: +44 (0) 1942 617000 Fax: +44 (0) 1942 617001	Revision date	16.09.2015	Page 2 of 2
	Product name	Hylomar M Issue 10	